p: 410-392-2300f: 410-392-2324e: info@aguafin.net

w: www.aquafin.net



Technical Datasheet

InjectProECO-CombiGrout

Hydrophobic, tough polyurethane grout for curtain grouting and void filling

No harmful phthalates

CSI Div. 03

03 64 00 Injection Grouting

Product Description:

InjectProECO-CombiGrout is a slightly flexible, tough, closed cell, polyurethane injection grout designed for grouting into voids and cracks. When it comes in contact with water, the grout expands and quickly cures to a tough, flexible, closed-cell polyurethane foam that is generally unaffected by common corrosive environments and is not subject to shrinkage due to wet/dry cycles. InjectProECO grouts are all environmentally friendly and formulated without harmful phthalates or VOC's.

The system is comprised of an "A" component (base resin) and a "B" component (accelerator). The "B" component is used by the applicator to adjust the set times for various job site specific conditions.

Typical Applications:

Typical applications include filling voids and sealing cracks with differential movement.

Advantages:

- Zero VOC's meets LEED criteria
- 100% solids, non-flammable, non-toxic permanent seal
- Hydrophobic can be used in wet and dry environments
- Expansion up to 20 times (free foam)
- Accelerator and resin stable to -40°F (-40°C).
- Flexible and tough foam
- Pumped as a single component
- Adjustable reaction times
- Non-hazardous shipping

Reaction Times & Use of Accelerator:

The reaction time can be adjusted by the addition of accelerator "B" into the base resin prior to pumping. The resulting profile is affected by temperature and the amount of moisture present.

Typical reaction times:

Accelerator %	Reaction	Polymerisation
6%	30 seconds	115 seconds
8%	25 seconds	90 seconds
10%	20 seconds	75 seconds

Installation Procedures:

Refer to the Aquafin InjectPro Grouting Guideline for full instructions. Mix both the resin (Component A) and accelerator (Component B) before combining.

- Pour the desired amount of InjectProECO-CombiGrout Resin Component A into a clean pail.
- Measure the appropriate amount of InjectProECO-ACCELERATOR-CCS Component B and pour into the InjectProECO-CombiGrout Resin, stirring until adequately mixed. Never use more accelerator than

Physical Properties			
Liquid (un-cured)	InjectProECO- CombiGrout Resin	InjectProECO- ACCELERATOR-CCS	
Color	Dark Amber	Clear	
Viscosity (ASTM D-1638)	250 cps	25 cps	
Specific Gravity (ASTM D-1475)	10 lbs/Gal (1.2 kg/L)	7.9 lbs/Gal (0.95 kg/L)	
Flash Point (ASTM D-92)	>250°F (>120°C)	225°F (107°C)	

Solid (cured) InjectProECO-CombiGrout		
Density (ASTM D-1622)	1 lbs/ft³ (~0.02 kg/dm³)	
Water Absorption (ASTM D-2842)	< 1%	
Elongation	60%	

recommended. Excess accelerator will cause significant expansion that is prone to shrinkage. For faster reaction times please contact technical services for information on InjectProECO-ACCELERATOR-CCS-FAST.

During injection, the grout will follow the path of least resistance. When the material has stopped penetrating it will continue to expand against the confines of the crack/joint and compress within itself, forming a very dense, closed cell material stopping the leak.

Packaging:

InjectProECO-CombiGrout Resin: 5 gallon pails (19 L) InjectProECO-ACCELERATOR-CCS: 32 oz. container (0.91 L) (5% dosage per 5 gallons (19 L)of resin. For 10% acceleration use 2 x 32 oz.) (2 x 0.91 L)

Storage & Shelf Life:

Shelf life is two years when stored properly. Product is highly moisture sensitive. Store in original sealed containers at temperature between 40°F – 90°F (4°C – 32°C). Opened containers must be handled properly to prevent moisture contamination.

Limitations:

- Temperature significantly affects viscosity. Protect material from excessive heating and cooling prior to grouting to avoid affecting viscosity.
- If using water baths to cool or heat pails avoid splashes to prevent water coming in direct contact with resin this will activate the reaction. Do not warm material or packaging above 90°F (32°C).
- Do not reseal containers of contaminated materials as it can create pressure.
- Clean up spills with adequate ventilation and appropriate personal
 protective equipment. Cover the spill area with absorbent material
 such as clay or vermiculite and transfer to metal waste containers.
 Wash area with decontamination solution (5-10% solution of sodium
 carbonate). Dispose of waste in accordance with federal, state and
 local regulations.

InjectProECO-CombiGrout

Note:

Proper application is the responsibility of the user. Field visits by AQUAFIN personnel are for the purpose of making technical recommendations and not for supervising or providing quality control on-site.

Safety:

Refer to SDS. For commercial use only. Avoid contact with skin and eyes. Wear rubber gloves and safety goggles during mixing and application. After contact with skin, wash with plenty of water. In case of eye contact, rinse immediately with plenty of water for 15 minutes and seek medical advice. KEEP OUT OF REACH OF CHILDREN.

LIMITED WARRANTY: AQUAFIN, INC. warrants this product for a period of one year from the date of installation to be manufactured free of defects and to be consistent with its technical properties as stated in our current Technical Data Sheet. This product must be used as directed and within its stated shelf life. AQUAFIN INC. will replace or at our discretion refund the purchase price of any product, excluding cost of labor, which is proven to be defective. Our product recommendations are based on industry standards and testing procedures. It is the buyer's obligation to test the suitability of the product for an intended use prior to using it. We assume no warranties written, expressed or implied as to any specific methods of application or use of the product. AQUAFIN INC. MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESS OR IMPLIED. AQUAFIN, INC. shall not be liable for damages of any sort including remote or consequential damages, down time, or delay. Any claim for a defective product must be filed within 30 days of discovery of a problem, and must be submitted with written proof of purchase.

For Professional Use Only.