

RE-ROOF Acrylic Top Coat

Single Component, Fast Drying, High-Performance, Acrylic Cool Roof Top Coat

CSI Div. 07 & 09

07 01 50 Maintenance of Membrane Roofing
 07 01 50.61 Roof Re-Coating
 07 14 16 Cold Fluid Applied Waterproofing
 09 01 90 Maintenance of Painting and Coating

LEED Points

MR Credit 5.1, Regional Materials.....Up to 2 Points
 IEQ Credit 4.2, Low-Emitting Materials Paints and Coatings...1 Point
 Using this AQUAFIN product can help contribute to LEED certification of projects in the categories shown above.

Product Description:

RE-ROOF Acrylic Topcoat is a single component, high-performing, liquid-acrylic coating that functions as a top coat for Aquafin's RE-ROOF Acrylic System. The RE-ROOF System is an eco-friendly, reliable solution for new roofs and cost-effective option for extending the life of existing roof systems.

Typical Applications:

- As the top coat for Aquafin's RE-ROOF Acrylic System.
- Apply RE-ROOF Acrylic Top Coat over RE-ROOF Acrylic Base Coat.

Advantages:

- Simple application with an airless sprayer, paint brush, or roller
- Excellent choice for warm, humid climates
- Resistant to mold growth

Preparation:

- RE-ROOF Acrylic Top Coat should only be applied over RE-ROOF Acrylic Base Coat. Refer to the RE-ROOF Acrylic Base Coat Technical Data Sheet for surface preparation instructions and other important information.
- Ensure RE-ROOF Acrylic Top Coat is applied within the required recoat time for RE-ROOF Acrylic Base Coat.
- The surface of RE-ROOF Acrylic Base Coat must be dry, clean and free of dirt, dust, grease, oil, and other foreign substances that could interfere with adhesion.

Jobsite Preparation:

- Take all necessary precautions to ensure safety.
- Cover all intake vents near the work area.
- Minimize or exclude all personnel not directly involved with the application.
- Follow appropriate measures to prevent any sparks.
- Do not weld, smoke or allow any open flames during mixing, application or drying.
- Ensure that CO2 or other dry chemical fire extinguishers are within easy access.
- Only proceed with application when ambient temperature is minimum of 50°F (10°C) and falling, and more than 6°F (3°C) above dew point. Temperatures must be maintained within this range for at least 48 hours after the installation. Do NOT proceed with application when the

Technical Properties:	
	RE-ROOF Acrylic Top Coat
Total Solids by Weight, ASTM D1644:	66 ± 2%
Total Solids by Volume, ASTM D2697:	54 ± 2%
Dry Adhesion ASTM C794, ASTM D903:	3.5 pli
Wet Adhesion ASTM C794, ASTM D903:	2.9 pli
Durometer Hardness Shore A, ASTM D2240:	65 - 75
Initial Tensile Strength, ASTM D2370:	310 ± 50 psi
Initial Elongation, ASTM D2370:	125 ± 25%
Elongation After Accelerated ASTM D2370:	125 ± 25%
Flexibility 1/8" Mandrel, ASTM D522:	Pass
Tear Resistance, Die C, ASTM D624:	70 pli
Permeance, ASTM D1653:	6 perms
Water Swelling, ASTM D471:	10 perms
1000 Hr Accelerated Weathering, ASTM D4798:	No Cracking or Checking
Fungi Resistance, ASTM G21:	Zero Growth
Colors:	Gray, Tan and White
VOCs:	0.39 lb/gal, 46 g/L
All data are averages of several tests under laboratory conditions. In practice climatic variations such as temperature, humidity, and porosity of substrate may affect these values.	

temperatures drop below 50°F (10°C), if precipitation is expected, or if humidity is at or above 90%. Coating should not become wet within 72 hours after application. Special precautions are to be taken when ambient and/or substrate temperatures are approaching, at, or above 105°F (41°C) and it may be necessary to limit material application to evening hours.

- Hot surfaces should be cooled and shaded while cold surfaces should be heated and sheltered.

RE-ROOF Acrylic Top Coat

Mixing:

- Condition material to 70°F to 80°F (21°C to 27°C) prior to mixing and application.
- Use chemical resistant (Nitrile) gloves and goggles when mixing or applying RE-ROOF Acrylic Top Coat.
- Open container and mix at slow speeds (not exceeding 500 rpm) for 1–2 minutes to evenly distribute pigments and other ingredients that may have settled, until a homogeneous mixture is achieved. Thoroughly scrape sides of pail as material is mixed. Boxing material is recommended to ensure color uniformity.
- Use caution not to whip air into the material as this may result in pinhole blisters and/or shortened pot life. Do not mix in an up and down motion.

Application:

Read all instructions thoroughly prior to installation.

- **Flashing Treatment:** Treat edges, seams, joints, metal flashing, penetrations and transitions with RE-ROOF Acrylic Flashing. Refer to the RE-ROOF Acrylic Flashing Technical Data Sheet for surface preparation, mixing and application instructions, WFT (wet film thickness) requirements, approx. coverage, drying and recoat times. Allow to dry and pay close attention to recoat times.
- **Primer:** Apply the appropriate primer to the field areas in preparation for RE-ROOF Acrylic Base Coat. Refer to the corresponding primer Technical Data Sheet for surface preparation, mixing and application instructions, DFT (dry film thickness) requirements, approx. coverage, drying and recoat times. Overlap the flashing according to the primer instructions. Allow to dry and pay close attention to recoat times.
- **First Base Coat:** Apply the first coat of RE-ROOF Acrylic Base Coat. Refer to the RE-ROOF Acrylic Base Coat Technical Data Sheet for surface preparation, mixing and application instructions, WFT (wet film thickness) requirements, DFT (dry film thickness) requirements, approx. coverage, drying and recoat times. Allow to dry and pay close attention to recoat times.
- **Second Base Coat:** Apply the second coat of RE-ROOF Acrylic Base Coat. Allow to dry and pay close attention to recoat times. Inspect the surface for damage prior to the application of RE-ROOF Acrylic Top Coat. Any surface damage must be repaired with RE-ROOF Acrylic Base Coat prior to the application of RE-ROOF Acrylic Top Coat.
- **First Top Coat:** Apply the first coat of RE-ROOF Acrylic Top Coat in a monolithic application at a rate of 72 ft²/gallon to achieve a minimum of 22 mils WFT (wet film thickness). Use an airless sprayer, paint brush, or phenolic resin core roller. Always backroll the first top coat with a roller, even when spray-applying. RE-ROOF Acrylic Top Coat must be a uniformly thick, void-free, continuous membrane across the entire roof surface. Allow to dry and pay close attention to recoat times.

Notes: Do not apply RE-ROOF Acrylic Top Coat at a rate of more than 1 gallon per 60 ft² (or more than 2 gallons per 120 ft²). Sagging and running is more likely to occur on sloped, slanted and vertical areas especially when the coating is applied to thick. Thicker coating applications also increase the chances of bubbles, blisters and/or pinholes. If necessary, apply RE-ROOF Acrylic Top Coat in several thinner coats, allowing each coat to properly dry. Always verify that the proper WFT (wet film thickness) has been achieved by measuring each coat using a wet film gauge. As a minimum, it is recommended to check the mil thickness in every corner, plus the center areas of the roof. Large areas will require many check points. When applying multiple, thinner coats, verify that the total DFT (dry film thickness) meets the stated requirements. See coverage chart for minimum WFT (wet film thickness) mil requirements and DFT (dry film thickness) mil requirements.

- **Second Top Coat:** Apply the second coat of RE-ROOF Acrylic Top Coat in a monolithic application at a rate of 72 ft²/gallon to achieve a

minimum of 22 mils WFT (wet film thickness). Always backroll the second top coat with a roller, even when spray-applying. Allow to dry and pay close attention to recoat times.

- **Third Top Coat:** Apply the third coat of RE-ROOF Acrylic Top Coat in a monolithic application at a rate of 72 ft²/gallon to achieve a minimum of 22 mils WFT (wet film thickness). Backroll to ensure uniform coverage. Allow to dry and pay close attention to recoat times.
- **Fourth Top Coat:** Apply the fourth coat of RE-ROOF Acrylic Top Coat in a monolithic application at a rate of 72 ft²/gallon to achieve a minimum of 22 mils WFT (wet film thickness). Do not backroll. Allow to dry and pay close attention to recoat times.

Total System Thickness (field areas): 66 mils DFT

Notes: Total system thickness requirement excludes additional dry mils of primer coat(s), and flashing.

Drying:

- Drying time for RE-ROOF Acrylic Top Coat is typically 24 hours at 75°F (24°C) and 50% relative humidity.
- Apply second coat and subsequent coats of RE-ROOF Acrylic Top Coat within a maximum of 48 hours after the underlying coat of RE-ROOF Acrylic Top Coat.
- Allow to dry for at least 72 hours [based on 75°F (24°C) and 50% relative humidity] before permitting light pedestrian traffic on the finished surface.

Limitations:

- Do not dilute under any circumstance.
- Do not apply over spray polyurethane foam roofing.
- High temperatures and high humidity will accelerate the drying time. Low temperatures and low humidity will extend the drying time.

Clean-up:

Clean tools and equipment with mineral spirits immediately after use, while still fresh/wet. Hardened/dried material must be removed mechanically.

Packaging:

- [5-gallon pail \(18.9 liters\)](#)
- [55-gallon drum \(208 liters\)](#)

Shelf Life & Storage:

- 12 months in unopened, original packaging when stored at temperatures between 50°F and 80°F (10°C to 27°C).
- Keep containers closed, store in a dry, cool place away from heat, direct sun, sparks, open flame, and moisture.
- Protect material from freezing.

Note:

Proper application is the responsibility of the user. Field visits by AQUAFIN personnel are for the purpose of making technical recommendations and not for supervising or providing quality control on-site.

Safety:

Refer to SDS. For commercial use only. Ensure adequate ventilation in application area. Use Type C organic vapor cartridge respirators during spray application. Vapor inhalation problems are characterized by coughing, shortening of breath and tightness in the chest. Anyone exhibiting these types of symptoms should be immediately removed from the workplace and administered oxygen or fresh air. If the condition is prolonged or extreme, seek emergency medical assistance immediately.


RE-ROOF Acrylic Top Coat

Avoid contact with skin and eyes. Wear fabric coveralls, neoprene gloves or other chemically resistant gloves and safety goggles during mixing and application. After contact with skin, wash with plenty of water. In case of eye contact, rinse immediately with plenty of water for 15 minutes and seek emergency medical assistance immediately. KEEP OUT OF REACH OF CHILDREN.

LIMITED WARRANTY: AQUAFIN, INC. warrants this product for a period of one year from the date of installation to be manufactured free of defects and to be consistent with its technical properties as stated in our current Technical Data Sheet. This product must be used as directed and within its stated shelf life. AQUAFIN INC. will replace or at our discretion refund the purchase price of any product, excluding cost of labor, which is proven to be defective. Our product recommendations are based on industry standards and testing procedures. It is the buyer's obligation to test the suitability of the product for an intended use prior to using it. We assume no warranties written, expressed or implied as to any specific methods of application or use of the product. AQUAFIN INC. MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESS OR IMPLIED. AQUAFIN, INC. shall not be liable for damages of any sort including remote or consequential damages, down time, or delay. Any claim for a defective product must be filed within 30 days of discovery of a problem, and must be submitted with written proof of purchase.

For Professional Use Only.

RE-ROOF Acrylic System Layers:



RE-ROOF Acrylic Top Coat - Coverage Rates				
WFT (wet film thickness) and DFT (dry film thickness) requirements are provided in mils				
	Minimum WFT (Wet Film Thickness)	Required DFT (Dry Film Thickness)	Coverage Rate Per Gallon	Coverage Rate Per Unit
1st Layer: Primer(s) for flashing area(s)	(see primer Technical Data Sheet)			
2nd Layer: 1st Coat Flashing: RE-ROOF Acrylic Flashing	25 mils		50 ft ²	175 ft ² (3.5 gal unit)
3rd Layer: (non-woven polyester reinforcing roof fabric)				
4th Layer: 2nd Coat Flashing: RE-ROOF Acrylic Flashing	25 mils		50 ft ²	175 ft ² (3.5 gal unit)
5th Layer: Primer for main field area (overlapping RE-ROOF flashing as instructed)	(see primer Technical Data Sheet)			
6th Layer: 1st Base Coat: RE-ROOF Acrylic Base Coat	17 mils	9 mils	94 ft ²	470 ft ² (5 gal unit)
7th Layer: 2nd Base Coat: RE-ROOF Acrylic Base Coat	17 mils	9 mils	94 ft ²	470 ft ² (5 gal unit)
8th Layer: 1st Top Coat: RE-ROOF Acrylic Top Coat	22 mils	12 mils	72 ft²	360 ft² (5 gal unit)
9th Layer: 2nd Top Coat: RE-ROOF Acrylic Top Coat	22 mils	12 mils	72 ft²	360 ft² (5 gal unit)
10th Layer: 3rd Top Coat: RE-ROOF Acrylic Top Coat	22 mils	12 mils	72 ft²	360 ft² (5 gal unit)
11th Layer: 4th Top Coat: RE-ROOF Acrylic Top Coat	22 mils	12 mils	72 ft²	360 ft² (5 gal unit)
Actual coverage may vary due to texture, and absorption of substrate. Failure to achieve the required dry mil thickness will compromise the effectiveness of the product and void the warranty. It is the applicator's responsibility to verify that the required dry mil thickness has been attained.				

Check our website for the latest version of the Technical Datasheet. Only the current version is legally binding - and only for the intended market. In cases of uncertainty contact our technical department for further information before starting any applications.